

Kormax 110 Copper

Material Data Sheet

110 Copper is a high purity material consisting of no less than 99.9% copper. Sometimes C11000 is also referred to as electrolytic tough pitch or ETP Copper.

All Kormax C11000 Copper is manufactured by a closely controlled extrusion process to ensure maximum electrical conductivity and formability.

Chemical Composition (%)

	Element		
Copper		Cu	99.9
Other			0.10 max

Mechanical Properties

	Metric Values
Tensile Strength Min	255 N/mm ²
Rockwell Hardness Min	77 HR

The technical data given in this sheet corresponds to our current state of knowledge and should not be construed as an agreement or guarantee regarding certain properties of our products. The decision on the suitability of a particular material for a specific application is up to the user. We reserve the right to modify the given data. Errors of the given data are reserved. The document was produced by machine and is valid without signature.