

Kormax Titanium Grade 5

Material Data Sheet

Titanium grade 5 (titanium-aluminium-vanadium alloy) is among the most widely used alpha-beta titanium alloys, comprising of 50% of total titanium used globally. One of the prominent properties of Titanium grade 5 is that it is entirely heat treatable, and can be used for the temperature up to 400°C. It combines low density (4.42kg/dm) with outstanding corrosion resistance and good mechanical strength.

Titanium grade 5 has excellent tensile properties at room temperature and has a good creep resistance up to 300°C. It also exhibits excellent resistance against crack propagation and fatigue. The age-hardening ability of titanium grade 5 makes it a perfect choice for various applications, including fasteners and spring. It has a wide range of industrial applications due to its good machinability and weldability.

Chemical Composition (%)

Element	Symbol	Range %
Aluminium	Al	5.5-6.75
Vanadium	V	3.5-4.5
Iron	Fe	0.4
Nitrogen	N ₂	0.05
Carbon	C	0.08
Oxygen	O ₂	0.02
Hydrogen	H ₂	0.30
Titanium	Ti	Balanced

Mechanical Properties

	Metric	Imperial
Tensile Strength min	895 MPa	129,809 psi
Yield Strength 0.2% min	828 MPa	120,091 psi
Elongation min	10%	10%
Area in reduction	25%	25%
Density	4.429 g/cm ³	

The technical data given in this sheet corresponds to our current state of knowledge and should not be construed as an agreement or guarantee regarding certain properties of our products. The decision on the suitability of a particular material for a specific application is up to the user. We reserve the right to modify the given data. Errors of the given data are reserved. The document was produced by machine and is valid without signature.